




Fly ash Test Report

United Kingdom

Technical Department

Portland House
Bickenhill Lane, Solihull
Birmingham. B37 7BQ

Telephone: 0845 812 6400
Facsimile: 0845 812 6200



Date: **16 August 2011**

Aberthaw

Fly ash BS EN 450-1

Fineness category:N, Loss on ignition category:A

Monthly average data for

January 2011

A) Physical and chemical properties of the fly ash sample

Test Property	Test result	BS EN 450-1
Fineness (%)	17.1	declared value 22.0
Sulfuric anhydride (%)	0.5	max 3.0
Loss on ignition (%)	3.6	0.0 to 5.0
Chloride (%)	0.00	max 0.1
Calcium oxide (%)	3.0	max 10.0
SiO ₂ +Al ₂ O ₃ +Fe ₂ O ₃ (%)	86.5	min 70.0
Free Lime (%)	0.28	max 1.0
Acid soluble alkali (%)	2.48	max 5.0
Additional information:		
Declared particle density (kg/m ³)	2280	

B) Physical properties of a 25:75 blend of the fly ash with a reference Portland cement

PC Source:

Ribblesdale

PC Initial setting time (min):

190

PC 28 day strength (MPa)

Test Property	Test result	BS EN 450-1
Activity index @ 28 days	82	min 75
Initial Setting Time (min)	225	max 120min more than PC

Note: This report has been produced from data supplied by the manufacturer, Celtic Ash

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager

Lafarge Cement UK PLC

Registered in England and Wales. Registered number 66558. Registered Office: Granite House, Granite Way, Syston, Leicester. LE1 1PL



Certificate of Conformity to BS 8500-2 Annex A

United Kingdom

Technical Department

Portland House
Bickenhill Lane
Solihull
Birmingham
B37 7BQ

Telephone: 0845 812 6400

Facsimile: 0845 812 6200

Date: **16 August 2011**

For a composite sample of

Aberthaw fly ash to BS EN 450-1

Fineness category:N, Loss on ignition category:A

prepared by Celtic Ash

and a composite sample of

Aberthaw PC-RM, BS EN 197-1 CEM I 52.5N

prepared by Lafarge Cement UK

each relating to product supplied during

January 2011

the results of test carried out in accordance with
BS 196-1 on a 70:30 blend of the CEM I with the
fly ash were

2 day strength	18.5	MPa
28 day strength	43.4	MPa

Based on equivalent results obtained for the last **11** months
the permitted proportion of combinations conforming with the requirements
of Annex A of BS 8500-2 are

Strength class of combination	fly ash content (as a percentage)	
	min	max
32,5 R	13	37
42,5 N	0	23

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager



United Kingdom

Certificate of Conformity to BS 8500-2 Annex A

Technical Department

Portland House
Bickenhill Lane
Solihull
Birmingham
B37 7BQ

Telephone: 0845 812 6400

Facsimile: 0845 812 6200

Date: **16 August 2011**

For a composite sample of

Aberthaw fly ash to BS EN 450-1

Fineness category:N, Loss on ignition category:A

prepared by Celtic Ash

and a composite sample of

Hope PC-RM, BS EN 197-1 CEM I 52,5N

prepared by Lafarge Cement UK

each relating to product supplied during

January 2011

the results of test carried out in accordance with
BS 196-1 on a 70:30 blend of the CEM I with the
fly ash were

2 day strength	20.5	MPa
28 day strength	43.5	MPa

Based on equivalent results obtained for the last **11** months
the permitted proportion of combinations conforming with the requirements
of Annex A of BS 8500-2 are

Strength class of combination	fly ash content (as a percentage)	
	min	max
32,5 R	19	39
42,5 N	5	26

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager



Certificate of Conformity to BS 8500-2 Annex A

United Kingdom

Technical Department

Portland House
Bickenhill Lane
Solihull
Birmingham
B37 7BQ

Telephone: 0845 812 6400

Facsimile: 0845 812 6200

Date: **16 August 2011**

For a composite sample of

Aberthaw fly ash to BS EN 450-1

Fineness category:N, Loss on ignition category:A

prepared by Celtic Ash

and a composite sample of

Castle Padeswood PC

prepared by Lafarge Cement UK

each relating to product supplied during

January 2011

the results of test carried out in accordance with
BS 196-1 on a 70:30 blend of the CEM I with the
fly ash were

2 day strength	19.1	MPa
28 day strength	43.4	MPa

Based on equivalent results obtained for the last **11** months
the permitted proportion of combinations conforming with the requirements
of Annex A of BS 8500-2 are

Strength class of combination	fly ash content (as a percentage)	
	min	max
32,5 R	19	34
42,5 N	0	23

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager



United Kingdom

Certificate of Conformity to BS 8500-2 Annex A

Technical Department

Portland House
Bickenhill Lane
Solihull
Birmingham
B37 7BQ

Telephone: 0845 812 6400

Facsimile: 0845 812 6200

Date: **16 August 2011**

For a composite sample of

Aberthaw fly ash to BS EN 450-1

Fineness category:N, Loss on ignition category:A

prepared by Celtic Ash

and a composite sample of

Cemex Rugby PC

prepared by Lafarge Cement UK

each relating to product supplied during

January 2011

the results of test carried out in accordance with
BS 196-1 on a 70:30 blend of the CEM I with the
fly ash were

2 day strength	20.4	MPa
28 day strength	45.2	MPa

Based on equivalent results obtained for the last **10** months
the permitted proportion of combinations conforming with the requirements
of Annex A of BS 8500-2 are

Strength class of combination	fly ash content (as a percentage)	
	min	max
32,5 R	15	37
42,5 N	0	25

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager



United Kingdom

Certificate of Conformity to BS 8500-2 Annex A

Technical Department

Portland House
Bickenhill Lane
Solihull
Birmingham
B37 7BQ

Telephone: 0845 812 6400

Facsimile: 0845 812 6200

Date: **16 August 2011**

For a composite sample of

Aberthaw fly ash to BS EN 450-1

Fineness category:N, Loss on ignition category:A

prepared by Celtic Ash

and a composite sample of

Dragon Alfa PC

prepared by Lafarge Cement UK

each relating to product supplied during

January 2011

the results of test carried out in accordance with
BS 196-1 on a 70:30 blend of the CEM I with the
fly ash were

2 day strength	18.2	MPa
28 day strength	41.6	MPa

Based on equivalent results obtained for the last **10** months
the permitted proportion of combinations conforming with the requirements
of Annex A of BS 8500-2 are

Strength class of combination	fly ash content (as a percentage)	
	min	max
32,5 R	15	35
42,5 N	0	24

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager



United Kingdom

Certificate of Conformity to BS 8500-2 Annex A

Technical Department

Portland House
Bickenhill Lane
Solihull
Birmingham
B37 7BQ

Telephone: 0845 812 6400

Facsimile: 0845 812 6200

Date: **16 August 2011**

For a composite sample of

Aberthaw fly ash to BS EN 450-1

Fineness category:N, Loss on ignition category:A

prepared by Celtic Ash

and a composite sample of

Lagerdorf PC

prepared by Lafarge Cement UK

each relating to product supplied during

January 2011

the results of test carried out in accordance with
BS 196-1 on a 70:30 blend of the CEM I with the
fly ash were

2 day strength	21.1	MPa
28 day strength	47.1	MPa

Based on equivalent results obtained for the last **8** months
the permitted proportion of combinations conforming with the requirements
of Annex A of BS 8500-2 are

Strength class of combination	fly ash content (as a percentage)	
	min	max
32,5 R	23	42
42,5 N	0	30

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager