




United Kingdom

Fly ash Test Report

Technical Department

Portland House
Bickenhill Lane, Solihull
Birmingham. B37 7BQ

Telephone: 0845 812 6400
Facsimile: 0845 812 6200



Date: **16 December 2009**

Cottam

Fly ash BS EN 450-1

Fineness category:S, Loss on ignition category:B

Monthly average data for **October 2009**

A) Physical and chemical properties of the fly ash sample

Test Property	Test result	BS EN 450-1
Fineness (%)	9.1	max 12.0
Sulfuric anhydride (%)	1.0	max 3.0
Loss on ignition (%)	4.3	2.0 to 7.0
Chloride (%)	0.01	max 0.1
Calcium oxide (%)	4.60	max 10.0
SiO ₂ +Al ₂ O ₃ +Fe ₂ O ₃ (%)	81.8	min 70.0
Free lime (%)	0.1	max 1.0
Acid soluble alkali (%)	3.30	max 5.0

Additional information:

Colour index	4
Declared particle density (kg/m ³)	2255

B) Physical properties of a 25:75 blend of the fly ash with a reference Portland cement

PC Source: **Ribblesdale**

PC Initial setting time (min): **180**

PC 28 day strength (MPa) **55.2**

Test Property	Test result	BS EN 450-1
Water requirement (%)	93	max 95
Activity index @ 28 days	88	min 75
Initial setting time (min)	250	max 120min more than PC

Note: This report has been produced from data supplied by the manufacturer, Processing Ash LLP

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager

Lafarge Cement UK PLC

Registered in England and Wales. Registered number 66558. Registered Office: Granite House, Granite Way, Syston, Leicester. LE1 1PL



Certificate of Conformity to BS 8500-2 Annex A

United Kingdom

Technical Department

Portland House
Bickenhill Lane
Solihull
Birmingham
B37 7BQ

Telephone: 0845 812 6400

Facsimile: 0845 812 6200

Date: **16 December 2009**

For a composite sample of

Cottam fly ash to BS EN 450-1

Fineness category:S, Loss on ignition category:B

prepared by Processing Ash LLP

and a composite sample of

Cauldon PC-RM, BS EN 197-1 CEM I 52.5N

prepared by Lafarge Cement UK

each relating to product supplied during

October 2009

the results of test carried out in accordance with
BS 196-1 on a 70:30 blend of the CEM I with the
fly ash were

2 day strength	16.4	MPa
28 day strength	41.7	MPa

Based on equivalent results obtained for the last **12** months
the permitted proportion of combinations conforming with the requirements
of Annex A of BS 8500-2 are

Strength class of combination	fly ash content (as a percentage)	
	min	max
32,5 R	17	39
42,5 N	6	26

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager



United Kingdom

Certificate of Conformity to BS 8500-2 Annex A

Technical Department

Portland House
Bickenhill Lane
Solihull
Birmingham
B37 7BQ

Telephone: 0845 812 6400

Facsimile: 0845 812 6200

Date: **16 December 2009**

For a composite sample of

Cottam fly ash to BS EN 450-1

Fineness category:S, Loss on ignition category:B

prepared by Processing Ash LLP

and a composite sample of

Dragon Alpha

prepared by the manufacturer

each relating to product supplied during

October 2009

the results of test carried out in accordance with
BS 196-1 on a 70:30 blend of the CEM I with the
fly ash were

2 day strength	19.5	MPa
28 day strength	41.8	MPa

Based on equivalent results obtained for the last **12** months
the permitted proportion of combinations conforming with the requirements
of Annex A of BS 8500-2 are

Strength class of combination	fly ash content (as a percentage)	
	min	max
32,5 R	9	41
42,5 N	6	21

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager



Certificate of Conformity to BS 8500-2 Annex A

United Kingdom

Technical Department

Portland House
Bickenhill Lane
Solihull
Birmingham
B37 7BQ

Telephone: 0845 812 6400

Facsimile: 0845 812 6200

Date: **16 December 2009**

For a composite sample of

Cottam fly ash to BS EN 450-1

Fineness category:S, Loss on ignition category:B

prepared by Processing Ash LLP

and a composite sample of

Dunbar PC-RM, BS EN 197-1 CEM I 52,5N

prepared by Lafarge Cement UK

each relating to product supplied during

October 2009

the results of test carried out in accordance with
BS 196-1 on a 70:30 blend of the CEM I with the
fly ash were

2 day strength	16.3	MPa
28 day strength	41.5	MPa

Based on equivalent results obtained for the last **12** months
the permitted proportion of combinations conforming with the requirements
of Annex A of BS 8500-2 are

Strength class of combination	fly ash content (as a percentage)	
	min	max
32,5 R	18	37
42,5 N	7	25

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager



United Kingdom

Certificate of Conformity to BS 8500-2 Annex A

Technical Department

Portland House
Bickenhill Lane
Solihull
Birmingham
B37 7BQ

Telephone: 0845 812 6400

Facsimile: 0845 812 6200

Date: **16 December 2009**

For a composite sample of

Cottam fly ash to BS EN 450-1

Fineness category:S, Loss on ignition category:B

prepared by Processing Ash LLP

and a composite sample of

Hope PC-RM, BS EN 197-1 CEM I 52,5N

prepared by Lafarge Cement UK

each relating to product supplied during

October 2009

the results of test carried out in accordance with
BS 196-1 on a 70:30 blend of the CEM I with the
fly ash were

2 day strength	18.3	MPa
28 day strength	43.5	MPa

Based on equivalent results obtained for the last **12** months
the permitted proportion of combinations conforming with the requirements
of Annex A of BS 8500-2 are

Strength class of combination	fly ash content (as a percentage)	
	min	max
32,5 R	15	41
42,5 N	6	25

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager



United Kingdom

Certificate of Conformity to BS 8500-2 Annex A

Technical Department

Portland House
Bickenhill Lane
Solihull
Birmingham
B37 7BQ

Telephone: 0845 812 6400

Facsimile: 0845 812 6200

Date: **16 December 2009**

For a composite sample of

Cottam fly ash to BS EN 450-1

Fineness category:S, Loss on ignition category:B

prepared by Processing Ash LLP

and a composite sample of

Castle Ketton

prepared by the manufacturer

each relating to product supplied during

October 2009

the results of test carried out in accordance with
BS 196-1 on a 70:30 blend of the CEM I with the
fly ash were

2 day strength	17.5	MPa
28 day strength	43.2	MPa

Based on equivalent results obtained for the last **12** months
the permitted proportion of combinations conforming with the requirements
of Annex A of BS 8500-2 are

Strength class of combination	fly ash content (as a percentage)	
	min	max
32,5 R	17	44
42,5 N	6	27

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager



United Kingdom

Certificate of Conformity to BS 8500-2 Annex A

Technical Department

Portland House
Bickenhill Lane
Solihull
Birmingham
B37 7BQ

Telephone: 0845 812 6400

Facsimile: 0845 812 6200

Date: **16 December 2009**

For a composite sample of

Cottam fly ash to BS EN 450-1

Fineness category:S, Loss on ignition category:B

prepared by Processing Ash LLP

and a composite sample of

Castle Padeswood

prepared by the manufacturer

each relating to product supplied during

October 2009

the results of test carried out in accordance with
BS 196-1 on a 70:30 blend of the CEM I with the
fly ash were

2 day strength	17.9	MPa
28 day strength	41.3	MPa

Based on equivalent results obtained for the last **12** months
the permitted proportion of combinations conforming with the requirements
of Annex A of BS 8500-2 are

Strength class of combination	fly ash content (as a percentage)	
	min	max
32,5 R	12	36
42,5 N	6	21

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager



United Kingdom

Certificate of Conformity to BS 8500-2 Annex A

Technical Department

Portland House
Bickenhill Lane
Solihull
Birmingham
B37 7BQ

Telephone: 0845 812 6400

Facsimile: 0845 812 6200

Date: **16 December 2009**

For a composite sample of

Cottam fly ash to BS EN 450-1

Fineness category:S, Loss on ignition category:B

prepared by Processing Ash LLP

and a composite sample of

Paragon Chatham

prepared by the manufacturer

each relating to product supplied during

October 2009

the results of test carried out in accordance with
BS 196-1 on a 70:30 blend of the CEM I with the
fly ash were

2 day strength	19.4	MPa
28 day strength	47.6	MPa

Based on equivalent results obtained for the last **12** months
the permitted proportion of combinations conforming with the requirements
of Annex A of BS 8500-2 are

Strength class of combination	fly ash content (as a percentage)	
	min	max
32,5 R	23	45
42,5 N	9	32

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager



United Kingdom

Certificate of Conformity to BS 8500-2 Annex A

Technical Department

Portland House
Bickenhill Lane
Solihull
Birmingham
B37 7BQ

Telephone: 0845 812 6400

Facsimile: 0845 812 6200

Date: **16 December 2009**

For a composite sample of

Cottam fly ash to BS EN 450-1

Fineness category:S, Loss on ignition category:B

prepared by Processing Ash LLP

and a composite sample of

Castle Ribblesdale

prepared by the manufacturer

each relating to product supplied during

October 2009

the results of test carried out in accordance with
BS 196-1 on a 70:30 blend of the CEM I with the
fly ash were

2 day strength	16.9	MPa
28 day strength	44.9	MPa

Based on equivalent results obtained for the last **12** months
the permitted proportion of combinations conforming with the requirements
of Annex A of BS 8500-2 are

Strength class of combination	fly ash content (as a percentage)	
	min	max
32,5 R	17	42
42,5 N	6	27

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager



United Kingdom

Certificate of Conformity to BS 8500-2 Annex A

Technical Department

Portland House
Bickenhill Lane
Solihull
Birmingham
B37 7BQ

Telephone: 0845 812 6400

Facsimile: 0845 812 6200

Date: **16 December 2009**

For a composite sample of

Cottam fly ash to BS EN 450-1

Fineness category:S, Loss on ignition category:B

prepared by Processing Ash LLP

and a composite sample of

Cemex Rugby

prepared by the manufacturer

each relating to product supplied during

October 2009

the results of test carried out in accordance with
BS 196-1 on a 70:30 blend of the CEM I with the
fly ash were

2 day strength	17.9	MPa
28 day strength	45.6	MPa

Based on equivalent results obtained for the last **12** months
the permitted proportion of combinations conforming with the requirements
of Annex A of BS 8500-2 are

Strength class of combination	fly ash content (as a percentage)	
	min	max
32,5 R	16	39
42,5 N	6	25

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager



United Kingdom

Certificate of Conformity to BS 8500-2 Annex A

Technical Department

Portland House
Bickenhill Lane
Solihull
Birmingham
B37 7BQ

Telephone: 0845 812 6400

Facsimile: 0845 812 6200

Date: **16 December 2009**

For a composite sample of

Cottam fly ash to BS EN 450-1

Fineness category:S, Loss on ignition category:B

prepared by Processing Ash LLP

and a composite sample of

Cemex South Ferriby

prepared by Lafarge Cement UK

each relating to product supplied during

October 2009

the results of test carried out in accordance with
BS 196-1 on a 70:30 blend of the CEM I with the
fly ash were

2 day strength	19.2	MPa
28 day strength	42.5	MPa

Based on equivalent results obtained for the last **12** months
the permitted proportion of combinations conforming with the requirements
of Annex A of BS 8500-2 are

Strength class of combination	fly ash content (as a percentage)	
	min	max
32,5 R	12	36
42,5 N	6	22

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager



United Kingdom

Certificate of Conformity to BS 8500-2 Annex A

Technical Department

Portland House
Bickenhill Lane
Solihull
Birmingham
B37 7BQ

Telephone: 0845 812 6400

Facsimile: 0845 812 6200

Date: **16 December 2009**

For a composite sample of

Cottam fly ash to BS EN 450-1

Fineness category:S, Loss on ignition category:B

prepared by Processing Ash LLP

and a composite sample of

BLI Tunstead

prepared by Lafarge Cement UK

each relating to product supplied during

October 2009

the results of test carried out in accordance with
BS 196-1 on a 70:30 blend of the CEM I with the
fly ash were

2 day strength	18.1	MPa
28 day strength	44.4	MPa

Based on equivalent results obtained for the last **11** months
the permitted proportion of combinations conforming with the requirements
of Annex A of BS 8500-2 are

Strength class of combination	fly ash content (as a percentage)	
	min	max
32,5 R	15	41
42,5 N	6	25

For and on behalf of Lafarge Cement UK :

National Commercial Technical Manager