

CERTIFICATE OF TEST

For Pulverised fuel ash in accordance with
BS EN 450-1:2005. Fineness Category N Loss on Ignition Category A
Source : Longannet
 Sampling Period: - December 2009

Test	Units	Value
Fineness (Residue on 0,45 micron sieve) Declared Fineness 15%	%	15.60
Loss on Ignition	%	2.68
Particle Density Declared 2200Kg/M3	Kg/m ³	2290
*Initial Setting Time (Ratio – see below) 25% PFA –test cement	Mins.	1.7
28 day Activity Index	%	81.00
SiO ₂ + Al ₂ O ₃ + Fe ₂ O ₃	%	83.34
Sulphuric Anhydride	%	0.75
Chloride Content	%	0.01
Calcium Oxide Content	%	3.17
Alkali Na ₂ O EQ	%	2.03

* Represents ratio = Setting time of Test cement + EN450 / Setting time of test cement (Limit = 2)



Chris Bennett
Quality Manager



INVESTOR IN PEOPLE



ScotAsh Limited,
Longannet Power Station,
Kincardine FK10 4AA
Scotland.

Telephone: 01259 730110

Facsimile: 01259 731055