

# Cemergi™

## CEM III/A CONCRETE

### Mix Design



bringing materials to *life*™

Lafarge Cemergi Blastfurnace cement (CEM III/A 42,5L) can be used in most applications where conventional Portland cement (CEMI) is used. However, simply substituting CEM III/A for Portland cement, weight for weight, in an existing concrete mix design is not always appropriate. This note describes the key modifications to concrete mix design required to optimise the performance of concrete containing CEM III/A.

*However, when using CEM III/A for the first time, trial mixes are strongly recommended.*

When using Volumetric mixers, the mix designs or calibrations preset by the equipment manufacturer may not always be suitable for CEM III/A concrete. The slightly lower density of CEM III/A compared with Portland cement (see section on sand content below), in particular, may be an issue.

The manufacturer of the mixer unit should be contacted in order to make the necessary adjustments.

### Workability and water content

The smooth surface texture of the slag particles in CEM III/A reduces the water demand of the cement relative to Portland cement by about 3% for equivalent slump.

Water content (kg/m <sup>3</sup> )	
Portland cement	CEM III/A
160	155
180	175
200	195
220	215

The setting time of CEM III/A concrete is increased relative to Portland cement concrete. This also reduces the rate of slump loss.

### Strength and cement content

The appropriate cement content for concrete of a given 28 day cube strength and slump should be determined from trial mixes.

The cement content may differ from that of an equivalent Portland cement (CEM I) concrete in certain circumstances. In particular, where a high strength concrete is required, the cement content may be slightly higher than for CEM I. It should be noted that whilst CEM III/A concrete has relatively low early strength development, it will continue to gain significant strength after 28 days if properly cured.

In some cases it may be possible to take advantage of this post 28 days strength gain, by agreeing to specify the strength

at 56 days. This would lead to possible economies in cement content. Trial mixes are recommended to determine the 28–56 day strength gain.

### Sand content and sand grading

The typical particle density of CEM III/A at 3010 kg/m<sup>3</sup> is lower than that of Portland cement (3150 kg/m<sup>3</sup>). Consequently CEM III/A occupies a slightly greater volume than the same batch weight of Portland cement.

If CEM III/A is directly substituted for Portland cement, conventional practice would be to reduce the amount of sand in the concrete mix to maintain yield. However, in practical terms, the additional volume of the cement is almost fully offset by the reduction in water content, and no reduction in sand content is normally required.

As the slag particles in CEM III/A are more angular than those in Portland cement, there is a tendency towards enhanced bleeding. It is therefore important to look at the overall sand grading as well as just the sand content of the mix. If the amount of fine sand in the concrete is too low, this can increase the tendency towards higher bleed levels and may make the concrete more susceptible to plastic settlement cracking in slabs or floors. Possible remedies for excessive bleed include, reducing the water content of the mix, using slightly finer sand, or replacing a proportion of the normal sand with finer material. A minimum fines content (passing 300 microns), and including the cement, of 450 kg/m<sup>3</sup> is often recommended for concrete industrial floors.

## Use of admixtures

Most concrete admixtures, designed to be used with Portland cement, will work equally well in CEM III/A concrete and at similar dosage rates (in terms of ml admixture/100 kg of CEM III/A). However, any retarding properties of admixtures will be magnified when used with CEM III/A cements. The admixture producer should be contacted for advice in the event of any admixture related problems.

## Technical Support

Further information and advice on this product and the full range of Lafarge Cement products can be obtained through the contacts listed below.

The information in this datasheet is accurate at the time of printing, but Lafarge Cement UK reserve the right to amend details as part of their product development programme.

## For further information

### Technical helpline

Tel: 0845 812 6232


E-mail: [info@uk.lafarge.com](mailto:info@uk.lafarge.com)

### Customer services

Tel: 0845 812 6300

E-mail:

[customerservice@uk.lafarge.com](mailto:customerservice@uk.lafarge.com)



LAFARGE CEMENT UK LTD

Portland House  
Bickenhill Lane

Solihull, Birmingham  
B37 7BQ

Tel. 0845 812 6400

Fax 0845 812 6200

[www.lafarge.co.uk](http://www.lafarge.co.uk)

